





EMD5800 Nanosilver Ink


Key Attributes and Benefits:

- EMD5800 is an inkjettable nanosilver ink with superior conductivity and high print resolution for consistent printed electronics manufacturing
- Featuring outstanding jetting performance as well as monodispersion and low-temperature sintering properties, EMD5800 ensures reduced processing time
- EMD5800 exhibits adhesion to a variety of substrates, including polyimide, polyethylene terephthalate (PET), polycarbonate and polycarbonate/acrylonitrilebutadiene-styrene (PC/ABS)
- Compatible with most industrial and commercial printer heads

EMD5800 Nanosilver Ink for Printed Electonics	
Silver Content	40-50%
Binder	Oil-Based
Viscosity	6 - 8 cPs @25°C
Surface Tension	25 - 28 dynes/cm
Volume Resistivity	6 - 25 uΩ.cm
Sintering Temperature	100 - 150°C for 10 - 60 min.
Storage and Shelf Life	10-15°C, 3 months
Available Quantities	50mL or 1L Amber Jars

Major Applications:

- Highly flexible and conductive organic light-emitting diode (OLED) panels
- Thin-film photovoltaic designs, such as organic photovoltaic (OPV) materials
- Extremely conductive and flexible printed mobile antennas
- Highly conductive printed RFIDs
- Touch screen displays



Although the information presented here is believed to be reliable, Sun Chemical Corporation makes no representation or guarantee to its accuracy, completeness or reliability of the information. All recommendations and suggestions are made without guarantee, since the conditions of use are beyond our control. There is no implied warranty of merchantability or fitness for purpose of the product or products described herein. In no event shall Sun Chemical Corporation be liable for damages of any nature arising out of the use or reliance upon the information. Sun Chemical Corporation expressly disclaims that the use of any material referenced herein, either alone or in combination with other materials, shall be free of rightful claim of any third party including a claim of infringement. The observance of all legal regulations and patents is the responsibility of the user.

SUNCHEMICAL is either a registered trademark or trademark of Sun Chemical Corporation, registered in the United States of America and/or other countries. DIC is a trademark of DIC Corporation, registered in the United States of America and/or other countries and used with permission. Copyright © 2022 Sun Chemical Corporation. All rights reserved.

GR AMOO2 FFR22

