

broad compatibility and unlimited color combinations: Flexiverse Water Based Dispersions.



color you can count on.

The flagship of our Preparation lines, Flexiverse Water Based Dispersions are formulated with the highest quality pigments and resins for unsurpassed stability, compatibility and consistency. An expansive pallet offers vibrant color for a variety of applications.

Key attributes:

- High gloss
- Viscosity stability
- Consistent color
- Broad compatibility
- High tinting strength
- Shock resistance
- Stir in convenience

Unlimited applications include:

- Inks
- Paints & coatings
- Non-woven
- Textile
- Latex
- Paper coating
- And many more....

Flexiverse dispersions are high-solids, stir-in organic pigment preparations designed exclusively for water-based applications. Produced to a consistent color value and strength, this broadly compatible line includes a vast pigment selection giving formulators unlimited color combinations. Components include organic pigment, acrylic resin, water and preservative.

Sun's global footprint enables us to deliver solutions to local markets worldwide. We understand that our customers are unique and we work closely with each to understand their needs and help them to execute their strategies.

| | | Product Code 1/20 Tint Color Index Name Color Index Number | | | | Heat Fa | stness | Light Fastness | | | | | | |
|----------|-----------|--|-----------|------|--------|---------|---------|----------------|--------------|---------------|----------------|----------------|----------|------|
| Masstone | 1/20 Tint | | % Pigment | Acid | Alkali | Water | Ethanol | Glycol | Paraffin Wax | Soap Sandwich | 15 min @ 150°C | 30 min @ 150°C | Masstone | Tint |
| | | YFD-2187 Pigment Yellow 3 Cl# 11710 | 32.0 | 4-5 | 4-5 | 4-5 | 2-3 | 2-3 | 3 | 3 | 5 | 3-4 | 7 | 5 |
| | | YFD-2193 Pigment Yellow 12 CI# 21090 | 31.0 | 5 | 4-5 | 5 | 4-5 | 2-3 | 2 | 4-5 | 4-5 | 3-4 | 4-5 | 3-4 |
| | | YFD-1123 M0 Pigment Yellow 14 Cl# 21095 | 35.0 | 4-5 | 4-5 | 5 | 4 | 5 | 5 | 5 | 4-5 | 4-5 | 4-5 | 3-4 |
| | | YCD-2004 Pigment Yellow 14 Cl# 21095 | 38.0 | 4-5 | 4-5 | 5 | 4 | 5 | 5 | 5 | 4-5 | 4-5 | 4-5 | 3-4 |
| | | YFD-9123 Pigment Yellow 74 Cl# 11741 | 35.0 | 4 | 4 | 5 | 2 | 4 | 1-2 | 3-4 | 4 | 1-2 | 7-8 | 7 |
| | | YFD-9681 Pigment Yellow 65 CI# 11740 | 34.0 | 5 | 5 | 2 | 4 | 3 | 5 | 5 | 4 | 4 | 7-8 | 5-6 |
| | | YFD-1128 Pigment Yellow 83 Cl# 21108 | 35.0 | 4 | 3 | 5 | 5 | 5 | 5 | 4-5 | 5 | 5 | 7 | 5-6 |
| | | YFD-9586 Pigment Yellow 42 CI# 77492 | 55.0 | 4 | 5 | 5 | 5 | 5 | 5 | 5 | 4 | 4 | 8 | 8 |
| | | OFD-1176 Pigment Orange 5 Cl# 12075 | 29.0 | 4-5 | 4-5 | 4 | 2 | 2-3 | 2 | 4-5 | 5 | 5 | 6 | 3 |
| | | OFD-9260 Pigment Orange 13 CI# 21110 | 36.0 | 5 | 5 | 5 | 3-4 | 3-4 | 3-4 | 3-4 | 5 | 5 | 5-6 | 3 |
| | | OFD-1633 Pigment Orange 16 Cl# 21160 | 45.0 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 2 | 2 | 3-4 | 3 |

| | | Product Code nt Color Index Name Color Index Number | | Bleed Resistance Heat Fastnes | | | | | | | | | | |
|----------|-----------|---|-----------|-------------------------------|--------|-------|---------|--------|--------------|---------------|----------------|----------------|----------|------|
| Masstone | 1/20 Tint | | % Pigment | Acid | Alkali | Water | Ethanol | Glycol | Paraffin Wax | Soap Sandwich | 15 min @ 150°C | 30 min @ 150°C | Masstone | Tint |
| | | RCD-9108 Pigment Orange 46 CI# 15602 | 33.0 | 4 | 4 | 3 | 2-3 | 2 | 3 | 1-2 | 3-4 | 3 | 4-5 | 2 |
| | | RFD-1131 Pigment Red 48:1 CI# 15865:1 | 31.0 | 5 | 3-4 | 5 | 5 | 2-3 | 5 | 1 | 3-4 | 2-3 | 5 | 5 |
| | | RFD-1133 Pigment Red 48:2 CI# 15865:2 | 28.0 | 4 | 2-3 | 5 | 4 | 3-4 | 5 | 1 | 3-4 | 2-3 | 5 | 4-5 |
| | | RFD-0170 Pigment Red 170 CI# 12475 | 34.0 | 5 | 5 | 5 | 4 | 4 | 4 | 5 | 5 | 5 | 7 | 6 |
| | | RCD-2088 Pigment Red 188 Cl# 12467 | 36.0 | 5 | 5 | 5 | 4 | 4 | 4 | 5 | 5 | 5 | 7 | 6 |
| | | RCD-9930 Pigment Red 2 Cl# 12310 | 37.0 | 5 | 5 | 5 | 2-3 | 2-3 | 2 | 5 | 5 | 3 | 5 | 3-4 |
| | | RFD-2188 Pigment Red 266 CI# 12474 | 32.0 | 5 | 5 | 5 | 2-3 | 2-3 | 2 | 5 | 5 | 3 | 5 | 3-4 |
| | | RFD-4241 Pigment Red 22 CI# 12315 | 30.0 | 5 | 5 | 5 | 4 | 2 | 2-3 | 3-4 | 3-4 | 3 | 5 | 2-3 |
| | | RFD-1132 Pigment Red 210 Cl# 12477 | 32.0 | 5 | 5 | 5 | 4-5 | 4 | 4 | 5 | 5 | 5 | 6 | 5 |
| | | RCD-9117 Pigment Red 49:1 CI# 15630:1 | 27.0 | 4 | 2-3 | 5 | 2 | 1 | 5 | 1 | 3 | 3 | 3-4 | 3 |
| | | RCD-9210 Pigment Red 49:2 Cl# 15630:2 | 22.0 | 4 | 2-3 | 5 | 2 | 1 | 5 | 1 | 3 | 3 | 3-4 | 3 |

| | | | | | d Resistar | | Heat Fa | stness | Light Fastness | | | | | |
|----------|-----------|--|-----------|------|------------|-------|---------|--------|----------------|---------------|----------------|----------------|----------|------|
| Masstone | 1/20 Tint | Product Code Color Index Name Color Index Number | % Pigment | Acid | Alkali | Water | Ethanol | Glycol | Paraffin Wax | Soap Sandwich | 15 min @ 150°C | 30 min @ 150°C | Masstone | Tint |
| | | RCD-9272 Pigment Red 57:1 Cl# 15850:1 | 24.0 | 3 | 3-4 | 5 | 4 | 2 | 5 | 1 | 5 | 3 | 3-4 | 3-4 |
| | | RFD-9587 Pigment Red 57:1 Cl# 15850:1 | 30.0 | 3 | 3-4 | 5 | 4 | 2 | 5 | 1 | 5 | 3 | 3-4 | 3-4 |
| | | RFD-9664 Pigment Red 81:2 Cl# 45160:3 | 33.0 | 3-4 | 2-3 | 3-4 | 2-3 | 2-3 | 5 | 2-3 | 3-4 | 3 | 3 | 2 |
| | | RFD-4250 Pigment Red 169 Cl# 45160:2 | 33.0 | 3-4 | 3-4 | 3 | 3 | 1 | 5 | 1 | 3-4 | 2 | 3 | 2 |
| | | QFD-1146 Pigment Red 122 CI# 73915 | 32.0 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 8 | 8 |
| | | RFD-9577 Pigment Red 101 CI# 77491 | 57.0 | 4 | 4 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 8 | 8 |
| | | RFD-5104 Pigment Red 269 CI# 12466 | 35.0 | 5 | 5 | 5 | 5 | 4 | 4 | 5 | 5 | 5 | 6 | 6 |
| | | RFD-0254 Pigment Red 254 CI# 56110 | 35.0 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 8 | 7 |
| | | VFD-9431 Pigment Violet 3 CI# 42535:2 | 26.0 | 3 | 4 | 4 | 1 | 1 | 4 | 1 | 3 | 3 | 3 | 2 |
| | | VFD-5102 Pigment Violet 27 CI# 42535:3 | 25.0 | 2-3 | 2-3 | 4 | 1 | 1 | 5 | 1 | 3 | 3 | 3 | 2-3 |
| | | VFD-1157 Pigment Violet 23 Cl# 51319 | 38.0 | 5 | 5 | 5 | 4 | 5 | 5 | 5 | 4 | 4 | 8 | 7 |

| | | | | | | Bleed | d Resistar | | Heat Fastness | | Light Fastness | | | |
|----------|-----------|--|-----------|------|--------|-------|------------|--------|---------------|---------------|----------------|----------------|----------|------|
| Masstone | 1/20 Tint | Product Code Color Index Name Color Index Number | % Pigment | Acid | Alkali | Water | Ethanol | Glycol | Paraffin Wax | Soap Sandwich | 15 min @ 150°C | 30 min @ 150°C | Masstone | Tint |
| | | QFD-1180 Pigment Violet 19 CI# 73900 | 33.0 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 8 | 8 |
| | | BFD-1149 Pigment Blue 15:0 Cl# 74160 | 34.0 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 8 | 8 |
| | | BFD-1121 Pigment Blue 15:3 CI# 74160 | 36.0 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 8 | 8 |
| | | BFD-8153 Pigment Blue 15:3 CI# 74160 | 39.0 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 8 | 8 |
| | | BFD-2060 Pigment Blue 61 CI# 42765:1 | 33.0 | 5 | 2 | 5 | 2 | 2 | 5 | 2 | 5 | 3 | 3 | 3 |
| | | BFD-0016 Pigment Blue 16 CI# 74100 | 30.0 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 8 | 8 |
| | | BCD-9758 Pigment Blue 79 Cl# 741300 | 33.0 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 8 | 8 |
| | | GFD-1151 Pigment Green 7 CI# 74260 | 50.0 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 8 | 8 |
| | | WFD-5006 Pigment White 6 CI# 77891 | 65.0 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 8 | 8 |
| | | LFD-4343 Pigment Black 7 Cl# 77226 | 40.0 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 5 | 8 | 8 |



A partner who transforms with you.

innovation

Today's environment requires more than change. It demands transformation — and a partner who's willing to transform with you. Sun Chemical, a member of the DIC group, is a leading producer of packaging and graphic solutions, color and display technologies, functional products, electronic materials, and products for the automotive and healthcare industries. Together with DIC, Sun Chemical is continuously working to promote and develop sustainable solutions to exceed customer expectations and better the world around us. With combined annual sales of more than \$8.5 billion and 22,000+ employees worldwide, the DIC Group companies support a diverse collection of global customers. As you move forward into a world of stiffer competition, faster turnarounds, more complex demands and sustainable products, count on Sun Chemical to be your partner.

working for you.

Although the information presented here is believed to be reliable, Sun Chemical Corporation makes no representation or guarantee to its accuracy, completeness or reliability of the information. All recommendations and suggestions are made without guarantee, since the conditions of use are beyond our control. There is no implied warranty of merchantability or fitness for purpose of the product or products described herein. In no event shall Sun Chemical Corporation be liable for damages of any nature arising out of the use or reliance upon the information. Sun Chemical Corporation expressly disclaims that the use of any material referenced herein, either alone or in combination with other materials, shall be free of rightful claim of any third party including a claim of infringement. The observance of all legal regulations and patents is the responsibility of the user.

SUNCHEMICAL and FLEXIVERSE are either registered trademarks of Sun Chemical Corporation in the United States and/or other countries. DIC and FASTOGEN are trademarks of DIC Corporation, registered in the United States and/or other countries. Copyright © 2022 Sun Chemical Corporation. All rights reserved.

